



Invotec
5929 Lakeside Blvd
Indianapolis, IN 46278

Phone: (317) 290-5000, FAX: (317) 290-5011

PRODUCT DATA SHEET

DESCRIPTION:

InvoCor CI - 3035

Calcium Borosilicate

APPLICATIONS:

InvoCor CI – 3035 has been specifically designed as a corrosion inhibiting pigment typically used in alkyd based protective coating systems. Typical loading levels are usually between 5 – 15% by total formula weight. A secondary application for this product is for the improving the “lift resistance” of alkyd primers when used at levels of 1 – 2.5%.

InvoCor CI – 3035, as defined by TSCA, is a mixture. All components of this mixture are listed in the TSCA Chemical Substances Inventory, Canadian DSL, and EINECS. It is USDA approved and meets ASTM Specification D 4288-83, Type II.

TYPICAL PHYSICAL PROPERTIES:

pH: 10

Oil Absorption: 30

Specific Gravity: 2.7

Moisture: 1.5%

Hegman Grind: 5

Water Solubility: 0.3% @ 25°C

CUSTOMER NOTICE:

Invotec MA LLC provides this information in good faith but makes no representation as to its comprehensiveness. Our products are intended for industrial use only. We cannot foresee how each customer may use the product in connection with its manufacturing and/or sales operation. Therefore, we cannot and do not warrant that the product will produce the results desired or expected by each customer under varying circumstances. It is the ultimate responsibility of each customer to determine the suitability of the product. Therefore, we strongly urge customers to vigorously pursue their own testing program in order to determine the suitability of our product to meet their requirements.

Imagination × Ingenuity + Implementation

“True innovation is the product of *imagination* and *ingenuity* combined with the unique ability to *implement* results to the maximum benefit of all our valued stakeholders.”